

Bleached Hardwood Sulphate Pulp LS-1 / ECF quality

Typical analysis

Lp.	Indexes at 60° SR	
1	Breaking length, km, not less than	8.2
2	Tearing strength, cH, not less than	47
3	Brightness, % not less than	88
4	Shives	
	0.1 mm – 1.0 mm not more than	12
	1.0 mm – 2.0 mm not more than	0
	More than 2.0 mm	0
5	Folding strength, not less than	460
6	pH	5 – 7
7	Moisture, %, not more than	15

Packing: Pulp in sheet packed in bales.
Dimension of bale in cm: 80/60/45.
Dimension of sheet in cm: 80/60.
The weight of bale: 201 kg.

